

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 14788 (2000): Styrene-butadiene Rubber (SBR) - Emulsion- and Solution-polymerized Types - Evaluation Procedures [PCD 13: Rubber and Rubber Products]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



भारतीय मानक

स्टाइरिन ब्यूटाडाइन रबर (एस. बी. आर.) — इमल्सन
तथा विलयन-पॉलीमरकृत टाइप — मूल्यांकन प्रक्रियाएं

Indian Standard

STYRENE-BUTADIENE RUBBER (SBR) —
EMULSION- AND SOLUTION-POLYMERIZED
TYPES — EVALUATION PROCEDURES

ICS 83.060

© BIS 2000

BUREAU OF INDIAN STANDARDS
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 110002

NATIONAL FOREWORD

This Indian Standard which is identical with ISO 2322 : 1996 'Styrene-butadiene rubber (SBR) — Emulsion- and solution-polymerized types — Evaluation procedures' issued by the International Organization for Standardization (ISO) was adopted by the Bureau of Indian Standards on the recommendations of the Rubber Sectional Committee and approval of the Petroleum, Coal and Related Products Division Council.

The text of ISO standard has been proposed to be approved as suitable for publication as Indian Standard without deviations. Certain conventions are, however, not identical to those used in Indian Standards. Attention is particularly drawn to the following:

- a) Wherever the words 'International Standard' appear referring to this standard, they should be read as 'Indian Standard'.
- b) Comma (,) has been used as a decimal marker while in Indian Standards, the current practice is to use a point (.) as the decimal marker.

In this adopted standard, reference appears to certain International Standards for which Indian Standards also exist. The corresponding Indian Standards which are to be substituted in their place are listed below along with their degree of equivalence for the editions indicated:

<i>International Standard</i>	<i>Corresponding Indian Standard</i>	<i>Degree of Equivalence</i>
ISO 37:1994 Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties	IS 3400 (Part 1) : 1987 Methods of test for vulcanized rubbers: Part 1 Tensile stress-strain properties (<i>second revision</i>)	Technically equivalent with minor deviations
ISO 247:1990 Rubber — Determination of ash	IS 3660 (Part 3) : 1988 Methods of test for natural rubber: Part 3 Determination of ash (NR:3) (<i>second revision</i>)	do
ISO 248 : 1991 Rubbers, raw — Determination of volatile-matter content	IS 3660 (Part 2) : 1985 Methods of test for natural rubber : Part 2 Determination of volatile matter (NR:2) (<i>second revision</i>)	do
ISO 289-1:1994 Rubber, unvulcanized — Determinations using a shearing-disc viscometer — Part 1 : Determination of Mooney viscosity	IS 3660 (Part 7) : 1988 Methods of test for natural rubber : Part 7 Determination of Mooney viscosity (NR:8) (<i>second revision</i>)	do
ISO 471:1995 Rubber — Temperatures, humidities and times for conditioning and testing	IS 13867 : 1993 Rubber standard temperatures, humidities and times for the conditioning and time interval between vulcanization and testing of test pieces	do
ISO 1795 : 1992 Rubber, raw natural and synthetic — Sampling and further preparative procedures	IS 5599 : 1999 Rubber — Raw, natural and synthetic — Methods of sampling and sample preparation (<i>first revision</i>)	do
ISO 2393 : 1994 Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures	IS 3660 (Part 8) : 1999 Methods of test for natural rubber : Part 8 Mixing and vulcanization of rubber in standard compound (NR:9) (<i>second revision</i>)	do

(Continued on third cover)

Indian Standard

STYRENE-BUTADIENE RUBBER (SBR) — EMULSION- AND SOLUTION-POLYMERIZED TYPES — EVALUATION PROCEDURES

1 Scope

This International Standard specifies

- physical and chemical tests on raw rubbers;
- standard materials, standard test formulations, equipment and processing methods for evaluating the vulcanization characteristics of emulsion- and solution-polymerized styrene-butadiene rubbers (SBR), including oil-extended rubbers.

It applies to those rubbers listed in table 1 which are normally used in vulcanized form.

Table 1 — Types of raw styrene-butadiene rubber

Rubber (oil-extended or non-oil-extended)	Styrene		
	Type of copolymer	Total content % (m/m)	Block content % (m/m)
Series A			
1) Emulsion SBR	random	< 50	0
2) Solution SBR	random	< 50	0
3) Solution SBR	partial block	< 50	< 30
Series B			
1) Emulsion SBR	random	> 50	0
2) Solution SBR	random	> 50	0
3) Solution SBR	partial block	< 50	> 30

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 37:1994, *Rubber, vulcanized or thermoplastic — Determination of tensile stress-strain properties*.

ISO 247:1990, *Rubber — Determination of ash*.

ISO 248:1991, *Rubbers, raw — Determination of volatile-matter content.*

ISO 289-1:1994, *Rubber, unvulcanized — Determinations using a shearing-disc viscometer — Part 1: Determination of Mooney viscosity.*

ISO 471:1995, *Rubber — Temperatures, humidities and times for conditioning and testing.*

ISO 1795:1992, *Rubber, raw, natural and synthetic — Sampling and further preparative procedures.*

ISO 2393:1994, *Rubber test mixes — Preparation, mixing and vulcanization — Equipment and procedures.*

ISO 3417:1991, *Rubber — Measurement of vulcanization characteristics with the oscillating disc curemeter.*

ISO 5725-1:1994, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions.*

ISO 5725-2:1994, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method.*

ISO 6502:—¹⁾, *Rubber — Introduction and guide to the use of curemeters.*

ISO/TR 9272:1986, *Rubber and rubber products — Determination of precision for test method standards.*

ISO 11235:—²⁾, *Rubber compounding ingredients — Sulfenamide-type accelerators — Methods of test.*

ASTM D 412-92, *Test methods for vulcanized rubber and thermoplastic rubbers and thermoplastic elastomers — Tension.*

ASTM D 1646-95a, *Test methods for rubber — Viscosity, stress relaxation, and pre-vulcanization characteristics (Mooney viscometer).*

ASTM D 2084-93, *Test method for rubber property — Vulcanization characteristics using oscillating disk cure meter.*

ASTM D 3185-88(1994), *Test methods for rubber — Evaluation of SBR (styrene-butadiene rubber) including mixtures with oil.*

3 Sampling and further preparative procedures

3.1 Take a laboratory sample of approximately 1,5 kg by the method described in ISO 1795.

3.2 Prepare test portions in accordance with ISO 1795.

4 Physical and chemical tests on raw rubber

4.1 Mooney viscosity

Determine the Mooney viscosity in accordance with ISO 289-1 on a test portion prepared in accordance with the preferred method of ISO 1795 (unmilled test portion).

Record the result as ML(1 + 4) at 100 °C.

NOTES

1) If ML(1 + 4) at 100 °C exceeds 100 MU, the small rotor may be used and the result reported as MS(1 + 4) at 100 °C.

2) Alternatively, the Mooney viscosity may be determined on a test portion prepared by the mill massing procedure of ISO 1795. This method will give poorer reproducibility, however, and the results may be different.

4.2 Volatile matter

Determine the volatile-matter content by the hot-mill method or by the oven method as specified in ISO 248.

1) To be published. (Revision of ISO 6502:1991)

2) To be published.

4.3 Ash

Determine the ash in accordance with method A or method B of ISO 247:1990.

5 Preparation of the test mixes

5.1 Standard test formulations

The standard test formulations are given in table 2.

The materials shall be national or international standard reference materials.

If no standard reference material is available, the materials to be used shall be agreed by the parties concerned.

5.2 Alternative formulations for oil-extended types

ASTM D 3185 specifies the test formulations given in table 3 for evaluation of general-purpose, oil-extended SBR, according to the oil content of the rubber. These test formulations may be used as alternatives to the test formulations given in table 2.

5.3 Procedure

5.3.1 Equipment and procedure

Equipment and procedure for the preparation, mixing and vulcanization shall be in accordance with ISO 2393.

Two alternative mixing procedures are specified:

Method A — Mill mixing

Method C — Miniature internal mixer mixing

NOTE — A method B using an internal mixer for initial mixing and a mill for final mixing is presented in annex A for information only since insufficient experience has been gained with this method and the absence of information on precision does not allow it to be included as an integral part of the standard.

Table 2 — Test formulations

Material	Parts by mass	
	Series A	Series B
Styrene-butadiene rubber (SBR) (including oil in oil-extended SBR)	100,00	—
Type 1500 SBR ¹⁾	—	65,00
Series B SBR	—	35,00
Sulfur	1,75	1,75
Stearic acid	1,00	1,00
Current industry reference black ²⁾	50,00	35,00
Zinc oxide	3,00	3,00
TBBS ³⁾	1,00	1,00
	156,75	141,75

1) SBR 1500 EST, supplied by Enichem Elastomeri, Strada 3, Palazzo B1, 20090 Assago, Milan, Italy, is an example of a suitable product available commercially. This information is given for convenience of users of this International Standard and does not constitute an endorsement by ISO of the product named. Equivalent products may be used if they can be shown to lead to the same results.

2) Dried for 1 h at 125 °C ± 3 °C and stored in a tightly closed container.

3) *N-tert-butylbenzothiazole-2-sulfenamide*. This shall be supplied in powder form having an initial insoluble-matter content, determined in accordance with ISO 11235, of less than 0,3 %. The material shall be stored at room temperature in a closed container and the insoluble matter shall be checked every 6 months. If this is found to exceed 0,75 %, the material shall be discarded or recrystallized.

Table 3 — Alternative test formulations for oil-extended types

Formulation No.	Quantity (parts by mass)					
	1B	2B	3B	4B	5B	6B
Parts oil	25	37,5	50	62,5	75	$\gamma^1)$
Oil-extended rubber	125,00	137,50	150,00	162,50	175,00	$100 + \gamma$
Zinc oxide	3,00	3,00	3,00	3,00	3,00	3,00
Sulfur	1,75	1,75	1,75	1,75	1,75	1,75
Stearic acid	1,00	1,00	1,00	1,00	1,00	1,00
Current industry reference black ²⁾	62,50	68,75	75,00	81,25	87,50	$(100 + \gamma)/2$
TBBS ³⁾	1,25	1,38	1,50	1,63	1,75	$(100 + \gamma)/100$
	194,50	213,38	232,25	251,13	270,00	
Batch factor for mill mix	2,4	2,2	2,0	1,9	1,7	
Batch factor for miniature internal mixer mix						
Cam head	0,37	0,34	0,31	0,29	0,27	
Banbury head	0,328	0,298	0,273	0,252	0,234	

1) γ = parts oil by mass per 100 parts base polymer in oil-extended rubber.
2) Dried for 1 h at $125 \text{ }^\circ\text{C} \pm 3 \text{ }^\circ\text{C}$ and stored in a tightly closed container.
3) *N-tert-butylbenzothiazole-2-sulfenamide*. This shall be supplied in powder form having an initial insoluble-matter content, determined in accordance with ISO 11235, of less than 0,3 %. The material shall be stored at room temperature in a closed container and the insoluble matter shall be checked every 6 months. If this is found to exceed 0,75 %, the material shall be discarded or recrystallized.

5.3.2 Method A — Mill mixing procedure

The standard laboratory mill batch mass, in grams, shall be based on four times the formulation mass (i.e. $4 \times 156,75 \text{ g} = 627 \text{ g}$ or $4 \times 141,75 \text{ g} = 567 \text{ g}$). Maintain the surface temperature of the rolls at $50 \text{ }^\circ\text{C} \pm 5 \text{ }^\circ\text{C}$. Maintain a good rolling bank at the nip of the rolls during mixing. If this is not obtained with the nip settings specified hereunder, small adjustments to the mill openings may be necessary.

	Series A		Series B	
	Duration	Cumulative time	Duration	Cumulative time
	(min)	(min)	(min)	(min)
a) Homogenize series B rubbers with the mill opening set at 1,1 mm at a temperature of $100 \text{ }^\circ\text{C} \pm 5 \text{ }^\circ\text{C}$.	—	—	1,0	—
b) Band the rubber with the mill opening set at 1,1 mm and make 3/4 cuts every 30 s from alternate sides. After banding SBR 1500, add the rubber [homogenized as in 5.3.2 a)] and make 3/4 cuts from both sides every 30 s.	7,0	7,0	—	—
c) Add the sulfur slowly and evenly across the rubber.	2,0	9,0	8,0	9,0
d) Add the stearic acid. Make one 3/4 cut from each side.	2,0	11,0	2,0	13,0
e) Add the carbon black evenly across the mill at a uniform rate. When about half the black has been incorporated, open the mill to 1,4 mm and make one 3/4 cut from each side. Then add the remainder of the carbon black. Be certain to add the black that has dropped into the mill pan. When all the black has been incorporated, open the mill to 1,8 mm and make one 3/4 cut from each side.	12,0	23,0	12,0	25,0

	Series A		Series B	
	Duration	Cumulative time	Duration	Cumulative time
	(min)	(min)	(min)	(min)
f) Add the zinc oxide and the TBBS with the mill opening still at 1,8 mm.	3,0	26,0	3,0	28,0
g) Make three 3/4 cuts from each side.	2,0	28,0	2,0	30,0
h) Cut the batch from the mill. Set the mill opening to 0,8 mm and pass the rolled batch endwise through the rolls six times.	2,0	30,0	2,0	32,0
i) Sheet the batch to an approximate thickness of 6 mm by opening the mill and passing the stock through the mill four times, folding it back on itself each time. Determine the mass of the batch (see ISO 2393). If the mass of the batch differs from the theoretical value by more than 0,5 %, discard the batch and remix. Remove sufficient material for curemeter testing.				
j) Sheet the batch to approximately 2,2 mm for preparing test sheets or to the appropriate thickness for preparing ISO ring test pieces in accordance with ISO 37.				
k) Condition the batch for 2 h to 24 h after mixing and prior to vulcanizing, if possible at standard temperature and humidity as defined in ISO 471.				

5.3.3 Method C — Miniature internal mixer procedure

For a miniature internal mixer having a nominal mixing capacity of 64 cm³, a batch mass corresponding to 0,47 times the formulation mass (i.e. 0,47 × 156,75 g = 73,67 g) for series A rubbers or to 0,49 times the formulation mass (i.e. 0,49 × 141,75 g = 69,46 g) for series B rubbers has been found to be suitable.

Mix with the head temperature of the miniature internal mixer maintained at 60 °C ± 3 °C and the unloaded-rotor speed at 6,3 rad/s to 6,6 rad/s (60 rpm to 63 rpm).

Prepare the rubber by passing it once through a mill with the temperature set at 50 °C ± 5 °C and an opening of 0,5 mm. Cut the sheet into strips that are 25 mm wide.

NOTE — Compounding materials other than rubber, carbon black and oil may be added to miniature internal mixer batches more precisely and with greater ease if they are previously blended together in the proportions required by the formulation. Such blends may be made using a mortar and pestle, by mixing for 10 min in a biconical blender with intensifier bar turning, or by mixing in a blender for five 3 s periods and scraping the inside of the blender to dislodge materials stuck to the sides after each 3 s mix. A Waring blender has been found suitable for this method. Caution: if mixed longer than 3 s, the stearic acid may melt and prevent good dispersion.

	Duration	Cumulative time
	(min)	(min)
a) Load the rubber, lower the ram and allow the rubber to be masticated.	1,0	1,0
b) Raise the ram and add the preblended zinc oxide, sulfur, stearic acid and TBBS, taking care to avoid any loss. Then add the carbon black, sweep the orifice and lower the ram.	1,0	2,0
c) Allow the batch to mix.	7,0	9,0
d) Turn off the motor, raise the ram, remove the mixing chamber and discharge the batch. Record the maximum batch temperature. The final temperature of the batch discharged after 9 min shall not exceed 120 °C. If necessary, adjust the batch mass or the head temperature so that this condition is met.		
e) Pass the batch through a mill set at 50 °C ± 5 °C once at a 0,5 mm mill opening and then twice at a 3,0 mm mill opening.		
f) Determine the batch mass and record. If it differs from the theoretical value by more than 0,5 %, discard the batch.		
g) Cut a test piece for testing vulcanization characteristics in accordance with ISO 3417 if required. Condition the specimen for 2 h to 24 h at 23 °C ± 3 °C before testing.		

- h) If required, sheet the batch to approximately 2,2 mm for preparing test sheets or to the appropriate thickness for preparing ring test pieces in accordance with ISO 37. To obtain the effects of mill direction, pass the folded batch four times between mill rolls set at $50\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$ and the appropriate mill opening. Cool on a flat, dry surface.
- i) Condition the batch for 2 h to 24 h after mixing and prior to vulcanizing, if possible at standard temperature and humidity as defined in ISO 471.

6 Evaluation of vulcanization characteristics by a curemeter test

6.1 Using an oscillating-disc curemeter

Measure the following standard test parameters:

M_L , M_H at defined time, t_{s1} , $t'_c(50)$ and $t'_c(90)$

in accordance with ISO 3417, using the following test conditions:

oscillation frequency: 1,7 Hz (100 cycles per minute)
amplitude of oscillation: 1° of arc
selectivity: to be chosen to give at least 75 % of full-scale deflection at M_H
With some rubbers, 75 % may not be attainable
die temperature: $160\text{ }^{\circ}\text{C} \pm 0,3\text{ }^{\circ}\text{C}$
pre-heat time: none

6.2 Using a rotorless curemeter

Measure the following standard test parameters:

F_L , $F_{\max}$ at defined time, t_{s1} , $t'_c(50)$ and $t'_c(90)$

in accordance with ISO 6502, using the following test conditions:

oscillation frequency: 1,7 Hz (100 cycles per minute)
amplitude of oscillation: $0,5^{\circ}$ of arc
selectivity: to be chosen to give at least 75 % of full-scale deflection at $F_{\max}$
With some rubbers, 75 % may not be attainable
die temperature: $160\text{ }^{\circ}\text{C} \pm 0,3\text{ }^{\circ}\text{C}$
pre-heat time: none

7 Evaluation of tensile stress-strain properties of vulcanized test mixes

Vulcanize sheets at $145\text{ }^{\circ}\text{C}$ for three periods selected from a cure series of 15 min, 25 min, 35 min, 50 min and 75 min.

Alternatively, vulcanize sheets at $150\text{ }^{\circ}\text{C}$ for three periods selected from a cure series of 10 min, 15 min, 20 min, 25 min, 30 min, 35 min and 50 min. These conditions will give results different from the ones obtained by the recommended standard vulcanization conditions.

The three periods of cure selected shall cover the undercure, optimum cure and overcure of the rubber under test.

Condition the vulcanized sheets for 16 h to 96 h, at a standard temperature and, if possible, at a standard humidity as defined in ISO 471.

Measure the stress-strain properties in accordance with ISO 37.

NOTE — Method C provides sufficient compounded material for evaluation of the stress-strain properties of one vulcanized sheet.

8 Precision

8.1 Method A — Mill mixing

8.1.1 General

The precision calculations to express repeatability and reproducibility were performed in accordance with ISO/TR 9272. Consult this for precision concepts and nomenclature. Annex B gives guidance on the use of repeatability and reproducibility.

8.1.2 Precision details

8.1.2.1 An interlaboratory test programme (ITP) was organized in 1986. Two formulations with series A SBRs were selected:

A-1 with an oil-extended SBR, type 1712, and

A-2 with a non-oil-extended SBR, type 1500.

One formulation with a series B SBR was selected:

A-3 with a high-styrene SBR rubber.

Mixes of these formulations were made in each of the 13 laboratories participating in the ITP, on each of two days approximately one week apart. The mixes were prepared from special samples of all the necessary materials, sent to each laboratory prior to the actual testing. For each material, the samples were drawn from a uniform and homogeneous lot. Stress-strain tests were conducted on cured sheets of each of the mixes or compounds as specified by the test programme.

8.1.2.2 The modulus (stress at 300 %), tensile strength and percent elongation were determined on dumb-bell test pieces in accordance with ISO 37 and taking as the test result the median of five individual test determinations. The precision thus calculated is a type 2 precision, and the time period for repeatability and reproducibility is on a scale of days.

See annex C for comments on the precision results.

8.1.3 Precision results

The precision results are given in table 4. The symbols used in table 4 are defined as follows:

r = repeatability, in measurement units. This is the value below which the absolute difference between two within-laboratory test results may be expected to lie with a specified probability.

(r) = repeatability, in percent (relative).

The two test results are obtained using the same method on nominally identical test materials under the same conditions (same operator, apparatus and laboratory) and within a specified time period; unless stated otherwise, the probability is 95 %.

R = reproducibility, in measurement units. This is the value below which the absolute difference between two between-laboratory test results may be expected to lie with a specified probability.

(R) = reproducibility, in percent (relative).

The two test results are obtained using the same method on nominally identical test materials under different conditions (different operators, apparatus and laboratories) and within a specified time period; unless stated otherwise, the probability is 95 %.

Table 4 — Type 2 precision for stress-strain tests after mixing with a mill mixer

Compound or material	Average value	Within lab		Between labs	
		<i>r</i>	(<i>r</i>)	<i>R</i>	(<i>R</i>)
Modulus (300 %), MPa					
SBR A-2	12,3	1,62	13,1	3,83	31,1
SBR A-1	14,6	1,80	12,3	3,86	26,5
SBR A-3	16,0	2,36	14,8	6,12	38,2
Tensile strength, MPa					
SBR A-2	20,3	2,05	10,1	3,09	15,2
SBR A-3	23,4	4,70	20,1	4,70	20,1
SBR A-1	25,5	2,50	9,79	3,60	14,1
Percent elongation					
SBR A-3	434	52,0	11,9	200	46,2
SBR A-2	481	56,6	11,8	103	21,5
SBR A-1	481	51,6	10,7	66,2	13,8

8.2 Method C — Miniature internal mixer mixing

8.2.1 General

The precision results for the miniature internal mixer mixing procedure used in the determination of the Mooney viscosity, vulcanization characteristics and tensile stress-strain properties of vulcanized test mixes have been taken from ASTM D 3185. References to ASTM standards have been replaced by references to corresponding ISO standards. These precision statements have been prepared in accordance with ISO 5725-1 and ISO 5725-2.

8.2.2 Precision details

8.2.2.1 The type 2 precision of these test methods was determined from interlaboratory testing of two rubbers, type 1712 and type 1502. Seven laboratories mixed each rubber by the miniature internal mixer method on each of two days and then tested them.

8.2.2.2 Table 5 gives the basic precision data as obtained in the interlaboratory programme. The curemeter testing was conducted in accordance with ISO 3417. In ISO 5725 terminology, type 2 precision includes as components of variation the mixing and curing operations carried out in each laboratory.

8.2.2.3 The test result for curemeter testing (ISO 3417) is one measurement with the curemeter.

8.2.2.4 The test result for tensile testing (ISO 37) is the median of the results obtained on three dumb-bell specimens.

8.2.2.5 The test result for viscosity testing (ISO 289-1) is one measurement with the viscometer.

8.2.2.6 For guidance on the use of precision results, see annex B.

8.2.3 Precision results

The precision results are given in table 5.

For definitions of the symbols, see 8.1.3 and

s_r = within-laboratory standard deviation

s_R = between-laboratories standard deviation

Table 5 — Type 2 precision after mixing with a miniature internal mixer

Property	Units	Range of values	Within laboratories			Among (between) laboratories		
			s_r	r	$(r)^{1)}$	s_R	R	$R^{1)}$
Precision estimates for ISO 3417:1991 at 160 °C, 1,7 Hz and 1° amplitude								
M_L	dN·m	9,7 to 9,8	0,21	0,594	6,1	0,52	1,47	15,2
M_H	dN·m	32,5 to 43,8	0,77	2,18	5,7	2,21	6,25	16,4
t_{s1}	min	3,5 to 4,9	0,13	0,368	8,8	0,67	1,90	45,2
$t'(50)$	min	8,2 to 8,3	0,20	0,566	6,9	0,74	2,09	25,3
$t'(90)$	min	13,6 to 16,4	0,48	1,36	9,1	1,12	3,17	21,1
Precision estimates for ISO 37:1994 at 145 °C for 35 min								
Modulus (300 %)	MPa	8,7 to 13,8	0,62	1,75	15,6	1,55	4,39	39,0
Tensile strength	MPa	21,9 to 25,9	0,83	2,35	9,8	1,40	3,96	16,6
Percent elongation		504 to 599	16,2	45,8	8,3	67,7	191,0	34,7
Precision estimates for ISO 289-1:1994								
ML (1 + 4) at 100 °C		63,8 to 70,3	1,51	4,27	6,4	6,61	18,7	27,9
1) Mid-point of range has been used to calculate (r) and (R).								

9 Test report

The test report shall include the following information:

- a reference to this International Standard;
- all details necessary for the identification of the sample;
- the method used for the volatile-matter content determination (mill or oven);
- the method used for the ash determination (method A or method B of ISO 247);
- the reference materials used;
- the standard test formulation used;
- the mixing procedure used;
- the conditioning environment used in 5.3.2 k) or 5.3.3 i) and in clause 7;
- the reference standard and the time for M_H used for the curemeter test in clause 6;
- the vulcanization times and temperature used in clause 7;
- any unusual features noted during the determination;
- any operation not included in this International Standard or in the International Standards to which reference is made, as well as any operation regarded as optional;
- the results and the units in which they have been expressed;
- the date of the test.

Annex A

(informative)

Method B — Internal mixer for initial mixing and mill for final mixing

For an internal mixer of type A1 (see ISO 2393) having a nominal capacity of $1\,170\text{ cm}^3 \pm 40\text{ cm}^3$, a batch mass, in grams, corresponding to 8,5 times the formulation mass (i.e. $8,5 \times 156,75\text{ g} = 1\,332,37\text{ g}$) has been found to be suitable for series A rubbers while 9,5 times the formulation mass (i.e. $9,5 \times 141,75\text{ g} = 1\,346,62\text{ g}$) has been found to be suitable for series B rubbers. The speed of the fast rotor shall be set at $77\text{ rpm} \pm 10\text{ rpm}$.

The final temperature of the batch discharged after 5 min mixing time shall be between $150\text{ }^\circ\text{C}$ and $170\text{ }^\circ\text{C}$. If necessary, adjust the batch mass to achieve the mixing conditions specified.

During final mixing, maintain a good rolling bank at the nip of the rolls. If this is not attained with the nip settings specified, small adjustments to the mill openings may be necessary.

A.1 Stage 1 — Initial mixing procedure

	Duration	Cumulative time
	(min)	(min)
a) Adjust the temperature of the internal mixer to a starting temperature of $50\text{ }^\circ\text{C} \pm 3\text{ }^\circ\text{C}$. Close the discharge door, set the rotor and raise the ram.		
b) Load the rubber, lower the ram and allow the rubber to be masticated.	0,5	0,5
c) Raise the ram and load the zinc oxide, stearic acid and carbon black. Lower the ram.	0,5	1,0
d) Allow the batch to mix.	2,0	3,0
e) Raise the ram and clean the mixer throat and the top of the ram. Lower the ram.	0,5	3,5
f) Allow the batch to mix.	1,5	5,0
g) Discharge the batch.		
h) Immediately check the temperature of the batch with a suitable measuring device. If the temperature as measured falls outside the range $150\text{ }^\circ\text{C}$ to $170\text{ }^\circ\text{C}$, discard the batch. Pass the batch three times through a mill with a mill opening of 2,5 mm and a temperature of $50\text{ }^\circ\text{C} \pm 5\text{ }^\circ\text{C}$. Sheet the batch to an approximate thickness of 10 mm and determine the mass of the batch. If the mass differs from the theoretical value by more than 0,5 %, discard the batch and remix.		
i) Leave the batch for at least 30 min and up to 24 h, if possible at standard temperature and humidity as defined in ISO 471.		

A.2 Stage 2 — Final mill-mixing procedure

- a) The standard laboratory mill batch mass, in grams, shall be based on three times the formula mass.
- b) Set the mill temperature at $50\text{ }^{\circ}\text{C} \pm 5\text{ }^{\circ}\text{C}$ and the mill opening to 1,5 mm.

	Duration	Cumulative time
	(min)	(min)
c) Band the masterbatch on the slow roll.	1,0	1,0
d) Add the sulfur and the accelerator. Do not cut the band until the sulfur and accelerator are completely dispersed.	1,5	2,5
e) Make three 3/4 cuts from each side, allowing 15 s between each cut.	2,5	5,0
f) Cut the batch from the mill. Set the mill opening at 0,8 mm and pass the rolled batch endwise through the rolls six times, introducing it from each end alternately.	2,0	7,0
g) Sheet the batch to approximately 2,2 mm for preparing test slabs or to the appropriate thickness for preparing ISO ring test pieces in accordance with ISO 37. Determine the batch mass and record. If it differs from the theoretical value by more than 0,5 %, discard the batch.		
h) Condition the batch for 2 h to 24 h after mixing and prior to vulcanizing, if possible at standard temperature and humidity as defined in ISO 471.		

Annex B

(informative)

Guidance for using precision results

B.1 The general procedure for using precision results is as follows, with the symbol $|x_1 - x_2|$ designating a positive difference in any two measurement values (i.e. without regard to sign).

B.2 Enter the appropriate precision table (for whatever test parameter is being considered) at an average value (of the measured parameter) nearest to the "test" data average under consideration. This line will give the applicable r , (r) , R or (R) for use in the decision process.

B.3 With these r and (r) values, the following general repeatability statements may be used to make decisions.

B.3.1 For an absolute difference: The difference $|x_1 - x_2|$ between two test (value) averages, found on nominally identical material samples under normal and correct operation of the test procedure, will exceed the tabulated repeatability r on average not more than once in twenty cases.

B.3.2 For a percentage difference between two test (value) averages: the percentage difference

$$[|x_1 - x_2|/(x_1 + x_2)/2] \times 100$$

between two test values, found on nominally identical material samples under normal and correct operation of the test procedure, will exceed the tabulated repeatability (r) on average not more than once in twenty cases.

B.4 With these R and (R) values, the following general reproducibility statements may be used to make decisions.

B.4.1 For an absolute difference: The absolute difference $|x_1 - x_2|$ between two independently measured test (value) averages, found in two laboratories using normal and correct test procedures on nominally identical material samples, will exceed the tabulated reproducibility R not more than once in twenty cases.

B.4.2 For a percentage difference between two test (value) averages: The percentage difference

$$[|x_1 - x_2|/(x_1 + x_2)/2] \times 100$$

between two independently measured test (value) averages, found in two laboratories using normal and correct test procedures on nominally identical material samples, will exceed the tabulated reproducibility (R) not more than once in twenty cases.

Annex C

(informative)

Comments on precision results

C.1 Table 4 indicates that the repeatability and the reproducibility are equal for tensile strength for SBR A-3. Such an occurrence can develop with a small data base (only a few laboratories) when the day 1 vs day 2 variations are fairly substantial, combined with the situation in which the day 1 and day 2 average gives rise to a reduced lab-to-lab variation.

C.2 Another way in which repeatability can be equal to reproducibility is a situation in which two main within-laboratory error-generating mechanisms are operating, i.e. the distribution of the cell standard deviations s_{ij} is bi-modal. The existence of the second upper (higher-value) peak inflates the within-laboratory r and (r) and causes the two values r and R to be equal. For this particular ITP with 13 laboratories, the existence of a bi-modal distribution is the most probable cause.

C.3 Precision results obtained with SBR types other than those tested in this programme may be different.

(Continued from second cover)

ISO 3417 : 1991 Rubber — Measurement of vulcanization characteristics with the oscillating disc curemeter	Nil
ISO 5725-1 : 1994 Accuracy (trueness and precision) of measurement methods and results — Part 1 : General principles and definitions	Nil
ISO 5725-2 : 1994 Accuracy (trueness and precision) of measurement methods and results — Part 2 : Basic method for the determination of repeatability and reproducibility of a standard measurement method	Nil
ISO 6502 : ¹⁾ Rubber — Introduction and guide to the use of curemeters	Nil
ISO/TR 9272 : 1986 Rubber and rubber products — Determination of precision for test method standards	Nil
ISO 11235 : ²⁾ Rubber compounding ingredients — Sulfenamide-type accelerators — Methods of test	Nil
ASTM D 412-92 Test methods for vulcanized rubber and thermoplastic rubbers and thermoplastic elastomers — Tension	Nil
ASTM D 1646-95a Test methods for rubber — Viscosity, stress relaxation and prevulcanization characteristics (Mooney viscometer)	Nil
ASTM D 2084-93 Test method for rubber property — Vulcanization characteristics using oscillating disk cure meter	Nil
ASTM D 3185-88 (1994) Test methods for rubber — Evaluation of SBR (styrene-butadiene rubber) including mixtures with oil	Nil

In the case of ISO 3417:1991, ISO 5725-1:1994, ISO 6502:, ISO/TR 9272:1986, ISO 11235, ASTM D 412-92, ASTM D 1646-95a, ASTM D 2084-93 and ASTM D 3185-88(1994), the Technical Committee responsible for the preparation of this standard has reviewed their contents and has decided that they are acceptable for use in conjunction with this standard.

For tropical countries like India, the standard temperature and the relative humidity shall be taken as $27 \pm 2^\circ\text{C}$ and 65 ± 5 percent respectively.

In reporting the results of a test or analysis made in accordance with this standard, if the final value, observed or calculated, is to be rounded off, it shall be done in accordance with IS 2:1960 'Rules for rounding off numerical values (*revised*)'.

¹⁾ To be published (Revision of ISO 6502:1991).

²⁾ To be published.

Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Catalogue' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc : No. PCD 14 (1434).

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

BUREAU OF INDIAN STANDARDS

Headquarters :

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110 002
Telephones : 323 01 31, 323 33 75, 323 94 02

Telegrams : Manaksanstha
(Common to all offices)

Regional Offices :

Telephone

Central	: Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110 002	{ 323 76 17 323 38 41
Eastern	: 1/14 C. I. T. Scheme VII M, V. I. P. Road, Kankurgachi CALCUTTA 700 054	{ 337 84 99, 337 85 61 337 86 26, 337 91 20
Northern	: SCO 335-336, Sector 34-A, CHANDIGARH 160 022	{ 60 38 43 60 20 25
Southern	: C. I. T. Campus, IV Cross Road, CHENNAI 600 113	{ 235 02 16, 235 04 42 235 15 19, 235 23 15
Western	: Manakalaya, E9 MIDC, Marol, Andheri (East) MUMBAI 400 093	{ 832 92 95, 832 78 58 832 78 91, 832 78 92
Branches	: AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR. PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM.	